



MembraneSeries

PROPERTIES	TEST METHOD	RESULT	UNIT
Base Fabric			PES
Coating			PVC with PVDF Laccuer
Total Weight	DIN EN ISO 2286-2	1400	g/m ²
Width	DIN EN ISO 2286-1	250	cm
Tensile Strength (N/5 cm)	DIN 53354	7000 / 6200	warp / weft
Tear Resistance (N)	DIN 53363	1500 / 1100	warp / weft
Adhesion	DIN 53357	150	(N/5 cm)
Translucency at 550 nm	DIN 5036	3	%
Flame Retardant *	NFPA-701,DIN4102 NF P 92.503	PASS / B1 / M2	